

Boltaflex® Contract Upholstery

Grand Sierra

Product Specifications:

General	
Total Wt. – oz./sq. yd. (CFFA-700d)	24.0
Total Wt. – oz./lin. yd. (CFFA-700d)	36.0
Width (min.) – in. (CFFA-700a)	54"
Gauge	.05"
Topskin Thickness	.008"
Face Content	Vinyl

Backing	
Construction	Jersey Knit
Weight – oz./sq. yd.	3.0
Content	88% Polyester / 12% Cotton
Fiber Type	Spun

Adhesion (CFFA-3)	
Pounds/Inches (min.)	Warp 3 Fill 3

Tensile Strength (CFFA-17)	
Pounds (min.)	Warp 110 Fill 85

Elongation @ 15# (CFFA-17)	
(avg.)	Warp 5% Fill 25%

Trap Tear Strength (CFFA-16c)	
Pounds	Warp 25 Fill 25

Tack Strength (Stitch) (CFFA-14)	
Pounds (min.)	Warp 60 Fill 30

Performance Testing: meets or exceeds

Abrasion (CFFA-1a)	
Wyzenbeek, Wire Screen	No change @ 60,000 cycles
Wyzenbeek, Cotton Duck	No change @ 100,000 cycles
VW Abrasion (CTM)	Pass

Blocking (CFFA-4)	Pass
--------------------------	------

W-Flex (CFFA-10)	Pass
-------------------------	------

Crock (CFFA-7)	Pass
-----------------------	------

QUV	72 hours
------------	----------

Mildew Resistance – ASTM G-21	Pass
--------------------------------------	------

Cold Crack (CFFA-6a)	
Roller Temperature (5#)	-20°F

Flame Retardancy	
FMVSS-302	Pass
NFPA 701 Small Scale	Pass
California Tech. Bulletin 117	Pass
Fed. Std. A-A-2950 (Supercedes CCC-A-680A)	Pass
FAR 25.853B	Pass
Boston Fire Dept. IX-1	Pass
UFAC Fabric, Class 1	Pass

Miscellaneous

Application	Indoor
--------------------	--------

Finish	PreFixx® Protective Coating
---------------	-----------------------------



253 Mansfield Ave - Norton, MA 02766

(508) 285-2500

1-800-875-7780

Fax: (508) 285-2502

www.FullCirclePadding.com